

Tabel 1. Pengujian material dengan dua temperature

NO.	MATERIAL	TEMPERATUR / SUHU (°C) OVEN	WAKTU	TEMPERATUR / SUHU (°C) STEAM	WAKTU	HASIL
1.	LEATHER	75°C	35/SEC	100°C	15/SEC	BELUM SESUAI
2.	LEATHER	75°C	35/SEC	150°C	15/SEC	BELUM SESUAI
3.	LEATHER	75°C	35/SEC	200°C	15/SEC	SESUAI
4.	LEATHER	80°C	35/SEC	100°C	15/SEC	BELUM SESUAI
5.	LEATHER	80°C	35/SEC	150°C	15/SEC	BELUM SESUAI
6.	LEATHER	80°C	35/SEC	200°C	15/SEC	SESUAI
7.	LEATHER	85°C	35/SEC	100°C	15/SEC	BELUM SESUAI
8.	LEATHER	85°C	35/SEC	150°C	15/SEC	SESUAI
9.	LEATHER	85°C	35/SEC	200°C	15/SEC	SESUAI